


Pane 1	PLANICLEAR (4 mm) BIOCLEAR SC II
Cavity 1	ARGON (90%) / AIR (10%) / 16 mm
Pane 2	PLANITHERM TOTAL+ FG PLANICLEAR (4 mm)

Saint Gobain Glass


Tim Hanlon

07710 842 344

tim.hanlon2@saint-gobain.com

 **LUMINOUS FACTORS** CIE (15-2004)

Light transmission (TL %)	44 %
Outdoor reflection (RLe %)	21 %
Indoor (RLi %)	24 %

 **SOLAR FACTORS** EN410 (2011-04)


Solar factor (g)	0.43
Shading Coefficient (SC)	0.50

 **COLOR RENDERING** CIE (15-2004)

Transmission (Ra)	97.1
Reflection (Ra)	87.9

 **BURGLAR RESIST** EN356

Result :	NPD
----------	-----

 **ENERGY FACTORS** EN410 (2011-04)

Transmission (Te)	37 %
Reflection (Ree)	22 %
Indoor (Rei)	29 %
Absorption (AE1)	36 %
Absorption (AE2)	6 %

 **THERMAL TRANSMISSION** EN673 (2011-04)


Ug	1.2 W/m ² .K
0° related to vertical position	

 **MANUFACTURING SIZES**

Nominal thickness	24.0 mm
Weight	20 kg/m ²

 **PENDULUM RESISTANCE** EN12600

Result :	NPD
----------	-----

 **ACOUSTICS** EN12758

Acoustic values according to EN 12758 and from notified body -	Rw(C;Ctr) = 31(-1;-4) dB
OITC (ASTM E1332)	N/A
STC (ASTM E413)	N/A